

LD 1.9 BRAIDED DOOR GASKET

TEMPERATURE RATING

SHORT TERM **1500°F**

CONTINUOUS **1000°F**

MELTING POINT **2050°F**

COMPOSITION E- GLASS

COLOR WHITE

SUNLIGHT AND AGING RESISTANCE EXCELLENT

ACID RESISTANCE GOOD

ALKALI RESISTANCE POOR

ABRASION RESISTANCE FAIR

SOLVENT RESISTANCE EXCELLENT

ADVANTAGES

- WILL NOT BURN, SMOLDER, SHRINK, ROT OR MILDEW
- HIGH DIELECTRIC STRENGTH
- MAINTAINS HIGH TENSILE STRENGTH AT ELEVATED TEMPERATURES
- HIGHLY RESISTANT TO MOST CHEMICALS

THE INFORMATION PRESENTED IS INTENDED AS A SPECIFICATION GUIDE ONLY. MATERIALS SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING. NO WARRANTIES ARE EXPRESSED OR IMPLIED AS APPLICATION CONDITIONS ARE BEYOND OUR CONTROL.