

CERAMIC FIBER ROLLBOARD PAPER

MELTING POINT **3200°F**

USE LIMIT **2300°F**

THERMAL CONDUCTIVITY	Mean Temp.	BTU – in/hr/ft²/°F
	500°F	0.47
	800°F	0.71
	1300°F	1.19
	1600°F	1.67

LOI **6%**

DENSITY **10 lbs / ft³**

DIELECTRIC STRENGTH **50 V / mil**

TENSILE STRENGTH

CD

MD **5000 g / in**
4000 g / in

CHEMICAL ANALYSIS (wt %)	Al₂O₃	46.50
	SiO₂	55.40
	OTHERS	0.10

NOMINAL THICKNESS **1/16", 1/10", 1/8"**

STANDARD WIDTH **24" & 48"**

- **A HIGH DENSITY PAPER MANUFACTURED FROM A BLEND OF SPUN ALUMINA SILICA FIBERS WITH REDUCED BINDER CONTENT TO MINIMIZE OFFGASSING AND ODOR DURING USE.**
- **GOOD HANDLING STRENGTH AND UNIFORMITY ASSURING HOMOGENOUS THERMAL CONDUCTIVITY.**
- **ITS FLEXIBILITY ALLOWS IT TO BE WRAPPED OR ROLLED TO FIT MOST COMPLEX CONFIGURATIONS**

THE INFORMATION PRESENTED IS INTENDED AS A SPECIFICATION GUIDE ONLY. MATERIALS SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING. NO WARRANTIES ARE EXPRESSED OR IMPLIED AS APPLICATION CONDITIONS ARE BEYOND OUR CONTROL