



7210 C – 5th  
Street SE Calgary,  
Alberta T2H 2L9

**Technical Data Sheet**

Bus: 403-216-3300  
Fax: 403-216-3306  
www.temprotec.com

**TECSTAR® 32**



ANSI/FM 4950 \*  
WELDING CURTAIN

<b>TEMPERATURE RESISTANCE CONTINUOUS</b>	<b>1000° F</b>	
	<b>REMAINS STABLE TO 1500° F WITH VERMICULITE COATING</b>	
<b>BASE FABRIC AND WEAVE</b>	<b>100% FIBERGLASS / PLAIN</b>	
<b>COLOR AND COATING</b>	<b>BRONZE / VERMICULITE*</b>	
<b>BASE FABRIC WEIGHT</b>	<b>32 oz / yd<sup>2</sup></b>	
<b>BASE FABRIC THICKNESS</b>	<b>0.070"</b>	
<b>BASE CLOTH</b>	<b>100% FIBERGLASS YARNS</b>	
<b>COUNT</b>	<b>WARP: 19</b>	<b>FILL: 9</b>
<b>SIZE</b>	<b>40" &amp; 60" x 50 lyds</b>	<b>WIDTH OF FINISHED PRODUCT MAY BE NARROWER DUE TO SHRINKAGE DURING COATING</b>

\* VERMICULITE IS AN INORGANIC, CHEMICALLY INERT, NON-COMBUSTIBLE & ODORLESS COATING OTHER:

**MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION WHERE FLEXING  
APPLICATONS AT ELEVATED TEMPERATURES. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH  
THE MSDS BEFORE HANDLING**

TecStar® is a registered trademark of Tempro Tec Inc.

THE INFORMATION PRESENTED IS INTENDED AS A SPECIFICATION GUIDE ONLY. MATERIALS SHOULD BE TESTED FOR ITS SUITABILITY  
IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING.

NO WARRANTIES ARE EXPRESSED OR IMPLIED AS APPLICATION CONDITIONS ARE BEYOND OUR CONTROL.