



7210 C – 5th  
Street SE Calgary,  
Alberta T2H 2L9

**Technical Data Sheet**

Bus: 403-216-3300  
Fax: 403-216-3306  
www.temprotec.com

## TECSTAR<sup>®</sup> 6000

TEMPERATURE RESISTANCE CONTINUOUS **1000° F**

- REMAINS STABLE TO **1500° F** WITH VERMICULITE COATING

BASE FABRIC AND WEAVE	100% FIBERGLASS	
WEAVE	PLAIN	
FABRIC FINISH	VERMICULITE *	
BASE FABRIC WEIGHT	60.0 oz / yd <sup>2</sup>	
BASE FABRIC THICKNESS	0.125"	
NOMINAL COATED WEIGHT	61.80 oz / yd <sup>2</sup>	
COUNT	WARP: 10	FILL: 7
BASE FABRIC SIZE	40" & 60" x 50 lyds	WIDTH OF FINISHED PRODUCT MAY BE NARROWER DUE TO SHRINKAGE DURING COATING

\* VERMICULITE IS AN INORGANIC, CHEMICALLY INERT, NON-COMBUSTIBLE & ODORLESS COATING

*THE INFORMATION PRESENTED IS INTENDED AS A SPECIFICATION GUIDE ONLY. MATERIALS SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING. NO WARRANTIES ARE EXPRESSED OR IMPLIED AS APPLICATION CONDITIONS ARE BEYOND OUR CONTROL*