

## FIBERGLASS-TFE THREAD

	<u>E-12</u> 0.014"	<u>E-18</u> 0.017"	<u>E-24</u> 0.020"
YIELD	2975 yds / lb	2000 yds / lb	1475 yds / lb
AVERAGE BREAK STRENGTH	14 lbs	19 lbs	27 lbs
SPECIFICATIONS			MIL-C 20079H(SH) TYPE III, CLASS 3 ASTM D 4030-89
PACKAGING APPROX.	2.0 lbs / SPOOL	2.0 lbs / SPOOL	2.0 lbs / SPOOL
FEATURES	<ul style="list-style-type: none"><li>• CONTINUOUS FILAMENT FIBERGLASS THREAD COATED WITH PTFE (TEFLON)</li><li>• WILL NOT BURN, <b>-400°F TO 1000°F</b> (-204°C TO 538°C)</li><li>• UNAFFECTED BY FUNGI AND MOST ACIDS/ALKALIS</li><li>• FLEXIBLE, HIGH ABRASION RESISTANCE</li><li>• IMPROVED SEWABILITY</li></ul>		

THE INFORMATION PRESENTED IS INTENDED AS A SPECIFICATION GUIDE ONLY. MATERIALS SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING. NO WARRANTIES ARE EXPRESSED OR IMPLIED AS APPLICATION CONDITIONS ARE BEYOND OUR CONTROL.