

## TECSIL<sup>®</sup> 2400-1SAS SILICA



ANSI/FM 4950 \*  
WELDING BLANKETS

### TEMPERATURE RESISTANCE

BASE FABRIC CONTINUOUS USE **1800° F**

BASE FABRIC MELT TEMPERATURE **3000° F**

COATING TEMPERATURE **500° F**

### CONTENT

96% SILICA (MINIMUM) CLOTH WITH  
CURED SILICONE RUBBER ON ONE  
SIDE

### WEAVE

HERRINGBONE

### WEIGHT

29.0 oz / yd<sup>2</sup>

### THICKNESS

0.047"

### COUNT

WARP: 30

FILL: 22

### SIZE

36" x 50 lyds

### FEATURES

ONE SIDE REPELS OILS AND MOISTURE,  
THE OTHER PROTECTS FROM HEAT

**NOTE: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION WHERE FLEXING OR VIBRATION OCCURS AT ELEVATED TEMPERATURES.**

**\* NOTE: WELDING PADS MAY ALSO BE USED AS WELDING BLANKETS.**

TecSil<sup>®</sup> is a registered trademark of Temprow Tec Inc.

THE INFORMATION PRESENTED IS INTENDED AS A SPECIFICATION GUIDE ONLY. MATERIALS SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING. NO WARRANTIES ARE EXPRESSED OR IMPLIED AS APPLICATION CONDITIONS ARE BEYOND OUR CONTROL.