



7210 C – 5th  
Street SE Calgary,  
Alberta T2H 2L9

## Technical Data Sheet

Bus: 403-216-3300  
Fax: 403-216-3306  
www.temprotec.com

# TECSTAR<sup>®</sup> 24

### TEMPERATURE RESISTANCE

CONTINUOUS **1000° F**  
REMAINS STABLE TO **1500° F** WITH VERMICULITE COATING



APPROVED

ANSI/FM 4950\*  
WELDING CURTAINS

|                              |                                |  |
|------------------------------|--------------------------------|--|
| <b>BASE FABRIC AND WEAVE</b> | <b>100% FIBERGLASS / PLAIN</b> |  |
| <b>COLOR AND COATING</b>     | <b>BRONZE / VERMICULITE*</b>   |  |
| <b>BASE FABRIC WEIGHT</b>    | <b>24 oz / yd<sup>2</sup></b>  |  |
| <b>BASE FABRIC THICKNESS</b> | <b>0.055"</b>                  |  |
| <b>COUNT</b>                 | <b>WARP: 20</b>                | <b>FILL: 11</b>  |
| <b>SIZE</b>                  | <b>40" &amp; 60" x 50 lyds</b> | <b>WIDTH OF FINISHED PRODUCT<br/>MAY BE NARROWER DUE TO<br/>SHRINKAGE DURING COATING</b> |

\* VERMICULITE IS AN INORGANIC, CHEMICALLY INERT, NON-COMBUSTIBLE & ODORLESS COATING

NOTE: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION WHERE FLEXING OR VIBRATION OCCURS AT ELEVATED TEMPERATURES.

TecStar<sup>®</sup> is a registered trademark of Temprow Tec Inc.

THE INFORMATION PRESENTED IS INTENDED AS A SPECIFICATION GUIDE ONLY. MATERIALS SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING. NO WARRANTIES ARE EXPRESSED OR IMPLIED AS APPLICATION CONDITIONS ARE BEYOND OUR CONTROL.

© Copyright 2010 Temprow Tec<sup>®</sup> Inc

