



7210 C – 5th  
Street SE Calgary,  
Alberta T2H 2L9

## Technical Data Sheet

Bus: 403-216-3300  
Fax: 403-216-3306  
www.temprotec.com

# TECSTAR<sup>®</sup> 35



ANSI/FM 4950\*  
WELDING CURTAINS

**TEMPERATURE RESISTANCE  
CONTINUOUS**

**1000° F**

REMAINS STABLE TO **1500° F** WITH VERMICULITE COATING

**BASE FABRIC AND WEAVE**

100% FIBERGLASS / PLAIN

**COLOR AND COATING**

BRONZE / VERMICULITE\*

**BASE FABRIC WEIGHT**

35 oz / yd<sup>2</sup>

**BASE FABRIC THICKNESS**

0.080"

**BASE CLOTH**

100% FIBERGLASS YARNS

**COUNT**

WARP: 10

FILL: 6.5

**SIZE**

40" & 60" x 50 lyds

WIDTH OF FINISHED PRODUCT MAY  
BE NARROWER DUE TO SHRINKAGE  
DURING COATING

\* VERMICULITE IS AN INORGANIC, CHEMICALLY INERT, NON-COMBUSTIBLE & ODORLESS COATING

OTHER: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION WHERE FLEXING OR VIBRATION OCCURS AT ELEVATED TEMPERATURES. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING

TecStar<sup>®</sup> is a registered trademark of Temprow Tec Inc.

THE INFORMATION PRESENTED IS INTENDED AS A SPECIFICATION GUIDE ONLY. MATERIALS SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING. NO WARRANTIES ARE EXPRESSED OR IMPLIED AS APPLICATION CONDITIONS ARE BEYOND OUR CONTROL

