



7210 C – 5th Street SE
Calgary, Alberta T2H 2L9

Technical Data Sheet

Bus: 403-216-3300
Fax: 403-216-3306
www.temprotec.com

TECSTAR® 24



APPROVED

ANSI/FM 4950*
WELDING CURTAINS

TEMPERATURE RESISTANCE

CONTINUOUS **1000° F**
REMAINS STABLE TO **1500° F WITH VERMICULITE COATING**

BASE FABRIC AND WEAVE 100% FIBERGLASS / PLAIN

COLOR AND COATING BRONZE / VERMICULITE*

BASE FABRIC WEIGHT 24 oz / yd²

BASE FABRIC THICKNESS 0.055"

COUNT WARP: 20 FILL: 11

SIZE 40" & 60" x 50 lyds
WIDTH OF FINISHED PRODUCT
MAY BE NARROWER DUE TO
SHRINKAGE DURING COATING

* VERMICULITE IS AN INORGANIC, CHEMICALLY INERT, NON-COMBUSTIBLE & ODORLESS COATING

NOTE: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION WHERE FLEXING OR VIBRATION OCCURS AT ELEVATED TEMPERATURES.

TecStar® is a registered trademark of Temprow Tec Inc.

THE INFORMATION PRESENTED IS INTENDED AS A SPECIFICATION GUIDE ONLY. MATERIALS SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING. NO WARRANTIES ARE EXPRESSED OR IMPLIED AS APPLICATION CONDITIONS ARE BEYOND OUR CONTROL.

© Copyright 2010 Temprow Tec® Inc

