

TECSTAR[®] 6000-1ANSI/FM 4950
WELDING PADS ***TEMPERATURE RESISTANCE**

BASE FABRIC (CONTINUOUS)	1000° F
REMAINS STABLE TO	
(WITH VERMICULITE COATING)	1500° F
SILICONE COATING	500° F

BASE FABRIC	PLAIN WEAVE FIBERGLASS CLOTH TREATED WITH VERMICULITE*
--------------------	---

WEIGHT	75 oz / yd²
---------------	-------------------------------

THICKNESS	0.115"
------------------	---------------

TENSILE STRENGTH W x F	550 x 350 lbs / in	ASTM D-5035
-------------------------------	---------------------------	--------------------

TEAR STRENGTH W x F	150 x 100 lbs	ASTM D-5587
----------------------------	----------------------	--------------------

SIZE	40" & 60" x 50 lyds	WIDTH OF FINISHED PRODUCT MAY BE NARROWER DUE TO SHRINKAGE DURING COATING
-------------	--------------------------------	--

FEATURES	HIGH QUALITY, HEAVY-WEIGHT FIBERGLASS CLOTH, TREATED WITH VERMICULITE AND COATED ON ONE SIDE WITH A SILICONE RUBBER COMPOUND.
-----------------	--

*VERMICULITE IS AN INORGANIC, CHEMICALLY INERT, NON-COMBUSTIBLE & ODORLESS COATING

NOTE: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION WHERE FLEXING OR VIBRATION OCCURS AT ELEVATED TEMPERATURES.

*** NOTE: WELDING PADS MAY ALSO BE USED AS WELDING BLANKETS AND CURTAINS.**

TecStar[®] is a registered trademark of Temprow Tec Inc.

THE INFORMATION PRESENTED IS INTENDED AS A SPECIFICATION GUIDE ONLY. MATERIALS SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING. NO WARRANTIES ARE EXPRESSED OR IMPLIED AS APPLICATION CONDITIONS ARE BEYOND OUR CONTROL.