



7210 C – 5th Street SE
Calgary, Alberta T2H 2L9

Technical Data Sheet

Bus: 403-216-3300
Fax: 403-216-3306
www.temprotec.com

TECSTAR[®] 6000

TEMPERATURE RESISTANCE CONTINUOUS **1000° F**
REMAINS STABLE TO **1500° F** WITH VERMICULITE COATING



BASE FABRIC AND WEAVE 100% FIBERGLASS

WEAVE PLAIN

FABRIC FINISH VERMICULITE *

BASE FABRIC WEIGHT 60.0 oz / yd²

BASE FABRIC THICKNESS 0.125"

NOMINAL COATED WEIGHT 61.80 oz / yd²

COUNT WARP: 10 FILL: 7

BASE FABRIC SIZE 40" & 60" x 50 lyds WIDTH OF FINISHED PRODUCT MAY
BE NARROWER DUE TO SHRINKAGE
DURING COATING

ANSI/FM 4950 *
WELDING PADS

* VERMICULITE IS AN INORGANIC, CHEMICALLY INERT, NON-COMBUSTIBLE & ODORLESS COATING

THE INFORMATION PRESENTED IS INTENDED AS A SPECIFICATION GUIDE ONLY. MATERIALS SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING. NO WARRANTIES ARE EXPRESSED OR IMPLIED AS APPLICATION CONDITIONS ARE BEYOND OUR CONTROL

© Copyright 2010 Tempro Tec[®] Inc

