

## KEVLAR / STAINLESS STEEL THREAD

<b>SIZE:</b>	<b>S – 110 / 3 ply</b>	
<b>DENIER SIZE:</b>	<b>1194.5</b>	
<b>STRENGTH: Lbs.</b>	<b>(12.188)</b>	<b>27.40</b>
(cN)		
<b>ELONGATION</b>		<b>2.70</b>
Elongation at break (%)		
<b>YIELD PER POUND: Yds.</b>	<b>3,743</b>	
(Mtr.)	<b>(3,422)</b>	
<b>SHRINKAGE:</b>		
BOILING WATER:	<b>&lt;1%</b>	
HOT AIR	<b>&lt;.5%</b>	
<b>KEVLAR DECOMPOSITION TEMPERATURES:</b>		
DEGREES – F	<b>800 - 900</b>	
DEGREES – C	<b>427– 482</b>	
<b>NEEDLE SIZE:</b>	<b>140/22</b>	
<b>COLOUR:</b>	<b>NATURAL</b>	
<b>TWIST:</b>	<b>12 S x 6 Z</b>	
<b>FINISH:</b>	<b>TEFLON</b>	
<b>LUBRICANT:</b>	<b>SILICONE</b>	
<b>PUT – UP:</b>	<b>1 Lb. per spool</b>	

THE INFORMATION PRESENTED IS INTENDED AS A SPECIFICATION GUIDE ONLY. MATERIALS SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING. NO WARRANTIES ARE EXPRESSED OR IMPLIED AS APPLICATION CONDITIONS ARE BEYOND OUR CONTROL