



7210 C – 5th Street SE  
Calgary, Alberta T2H 2L9

**Technical Data Sheet**

Bus: 403-216-3300  
Fax: 403-216-3306  
www.temprotec.com

## TECSTAR<sup>®</sup> 24

### TEMPERATURE RESISTANCE

**CONTINUOUS** **1000° F**  
**REMAINS STABLE TO** **1500° F WITH VERMICULITE COATING**

**BASE FABRIC AND WEAVE** 100% FIBERGLASS / PLAIN

**COLOR AND COATING** BRONZE / VERMICULITE\*

**BASE FABRIC WEIGHT** 24 oz / yd<sup>2</sup>

**BASE FABRIC THICKNESS** 0.055"

**COUNT** WARP: 20 FILL: 11

**SIZE** 40" & 60" x 50 lyds  
WIDTH OF FINISHED PRODUCT  
MAY BE NARROWER DUE TO  
SHRINKAGE DURING COATING

\* VERMICULITE IS AN INORGANIC, CHEMICALLY INERT, NON-COMBUSTIBLE & ODORLESS COATING

**NOTE: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION WHERE FLEXING OR VIBRATION OCCURS AT ELEVATED TEMPERATURES.**

TecStar<sup>®</sup> is a registered trademark of Tempro Tec Inc.

*THE INFORMATION PRESENTED IS INTENDED AS A SPECIFICATION GUIDE ONLY. MATERIALS SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING. NO WARRANTIES ARE EXPRESSED OR IMPLIED AS APPLICATION CONDITIONS ARE BEYOND OUR CONTROL.*

© Copyright 2010 Tempro Tec<sup>®</sup> Inc

